Zr 掺杂对 La(Ba)Zr_xCo_{1-x}O_{3-δ} 钙钛矿催化 N₂O 分解性能的影响刘 爽^{1,2}, 丛 昱¹, Charles KAPPENSTEIN^{1,3}, 张 涛^{1,*}¹ 中国科学院大连化学物理研究所催化基础国家重点实验室, 辽宁大连 116023² 中国科学院研究生院, 北京 100049³ 普瓦提大学环境与材料化学研究所, 法国普瓦提 86022

摘要: 采用溶胶凝胶法制备了 Zr 掺杂的钴基钙钛矿 La(Ba)Zr_xCo_{1-x}O_{3-δ}, 并将其用于航天推进剂领域的高浓度 N₂O 催化分解反应. 发现 Zr 的引入明显提高了钙钛矿 La(Ba)Zr_xCo_{1-x}O_{3-δ} 的催化活性, 尤其是当 Zr 掺杂量分别为 0.05 和 0.2 时, LaZr_xCo_{1-x}O_{3-δ} 和 BaZr_xCo_{1-x}O_{3-δ} 催化剂性能较为优异. 应用 N₂ 物理吸附、X 射线衍射、H₂ 程序升温还原、O₂ 程序升温脱附和氧脉冲吸附技术表征了 Zr 掺杂对 La(Ba)Zr_xCo_{1-x}O_{3-δ} 催化剂的物化性质的影响. 结果表明, Zr 掺杂增大了钴基钙钛矿的比表面积, 改善了晶格结构, 从而提高了钴物种的还原及氧吸附脱附能力, 因而催化剂上 N₂O 分解活性增加.

关键词: 钴酸镧; 钴酸钡; 锆; 氧化亚氮; 分解

中图分类号: O643 文献标识码: A

收稿日期: 2012-03-15. 接受日期: 2012-04-12.

*通讯联系人. 电话: (0411)84379015; 传真: (0411)84685940; 电子信箱: taozhang@dicp.ac.cn

基金来源: 国家自然科学基金 (20973165); 中国科学院对外合作重点项目 (GJHZ200827).

本文的英文电子版(国际版)由Elsevier出版社在ScienceDirect上出版(<http://www.sciencedirect.com/science/journal/18722067>).

Effect of Zirconium in La(Ba)Zr_xCo_{1-x}O_{3-δ} Perovskite Catalysts for N₂O DecompositionLIU Shuang^{1,2}, CONG Yu¹, Charles KAPPENSTEIN^{1,3}, ZHANG Tao^{1,*}¹ State Key Laboratory of Catalysis, Dalian Institute of Chemical Physics, Chinese Academy of Sciences, Dalian 116023, Liaoning, China² Graduate University of Chinese Academy of Sciences, Beijing 100049, China³ Institute of Chemistry of Mediums and Materials of Poitiers, University of Poitiers, Poitiers 86022, France

Abstract: Zr-incorporated La(Ba)Zr_xCo_{1-x}O_{3-δ} perovskites were prepared by a sol-gel method and used for the catalytic decomposition of the high concentrations of N₂O present in propulsion applications. The introduction of Zr significantly enhanced N₂O conversion, esp. with $x = 0.05$ and 0.2 for LaZr_xCo_{1-x}O_{3-δ} and BaZr_xCo_{1-x}O_{3-δ}, respectively. N₂ adsorption, X-ray diffraction, temperature-programmed reduction of H₂, temperature-programmed desorption of O₂, and oxygen pulse chemisorption techniques were used to characterize the structure and redox and oxygen adsorption property of the perovskites. The increasing of the surface area, modifying of the crystal structure, more facile reducibility of cobalt species, and higher oxygen desorption-adsorption activity due to the introduction of Zr were the reasons for the activity enhancement for N₂O decomposition.

Key words: lanthanum cobaltate; barium cobaltate; zirconium; nitrous oxide; decomposition

Received 15 March 2012. Accepted 12 April 2012.

*Corresponding author. Tel: +86-411-84379015; Fax: +86-411-84685940; E-mail: taozhang@dicp.ac.cn

This work was supported by the National Natural Science Foundation of China (20973165) and the External Cooperation Program of Chinese Academy of Sciences (GJHZ200827).

English edition available online at Elsevier ScienceDirect (<http://www.sciencedirect.com/science/journal/18722067>).

Nitrous oxide (N₂O) is a promising green propellant for space propulsion due to its low toxicity, self-pressurized

feeding characteristic, and multiple modes of propulsion application in comparison with the traditional hydrazine

propellant [1–3]. The activity and thermal stability of the catalyst are important criteria for use in the decomposition of N_2O owing to its high activation energy of 250 kJ/mol and enormous heat release that can lead to a maximum adiabatic temperature as high as 1600 °C [4,5]. It is very difficult to find a catalyst that simultaneously has the above two properties. Therefore, the development of an appropriate catalyst with high activity at low temperature and thermal stability at high temperature is a great challenge.

Two main methods have been used to develop catalytic materials for N_2O decomposition for propulsion applications. One is to stabilize noble metals on thermally stable supports. Such catalysts include Rh/Mullite [4], Rh/ $\text{Al}_2\text{O}_3\text{-SiO}_2$ [6], Ir/ $\text{Al}_2\text{O}_3\text{-TiO}_2$ [7], and Shell 405 [2], which display excellent initial activity at low temperatures and good thermal stability at high temperatures. The other method is to explore novel composite oxides possessing high thermal stability with special crystal structures, e.g., noble metal or transition metal substituted hexaaluminates have demonstrated reasonable activity and outstanding thermal stability [5,8–10].

Perovskite-type mixed oxides (general formula ABO_3) have much better thermal stability than common transition metal oxides [11,12] and their catalytic activities are sometimes competitive with supported noble metal catalysts [13]. Perovskites can be good catalysts for the desorption of oxygen, which is the rate determining step of N_2O decomposition [15] because of their high mobility and diffusivity of oxygen [14]. Good thermal stability, high activity, and unusual oxygen migration behavior make perovskite-based materials promising for the catalytic decomposition of N_2O . Surprisingly, there are few studies on N_2O decomposition on perovskites, and which were mainly focused on the removal of low concentration N_2O as a greenhouse gas [15]. Among these, LaCoO_3 is a highly active catalyst that decomposes N_2O completely below 600 °C [16]. The introduction of Sr into LaCoO_3 modified the oxygen vacancies and electronic configuration of the cobalt ions, and led to a higher activity for N_2O decomposition [17–19]. Other substitutions have also been investigated using Pb [20–22], Cu [23], K [24], Bi [25], Ba [25], and Zn [26] to improve lattice oxygen mobility, specific surface area, and catalytic activity. Yet, almost nothing has been reported on Zr incorporation. Yang et al. [27,28] reported that a perovskite-type oxygen permeable membrane with Zr substitution ($\text{BaZr}_{0.2}\text{Co}_{0.4}\text{-Fe}_{0.4}\text{O}_{3-\delta}$) displayed a much higher oxygen flux than that without Zr, and its thermal stability was enhanced by the less reducible Zr^{4+} ion. These findings inspired a strong interest in us to probe the effect of Zr introduction on the physicochemical properties of perovskites and catalytic performance in N_2O decomposition to develop a novel high performance catalyst.

In this work, cobalt-based perovskites with large cations La^{3+} and Ba^{2+} in the A site were chosen as the base catalysts for the reasons that LaCoO_3 has a comparatively high activity and Ba showed a promoting effect in the doping of the A site of LaCoO_3 in the oxidation of CO [29]. BaCoO_3 has not been studied as a catalyst for N_2O decomposition. Here, Zr-substituted $\text{LaZr}_x\text{Co}_{1-x}\text{O}_3$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_3$ perovskites were prepared by a sol-gel method. N_2 adsorption (BET), X-ray diffraction (XRD), temperature-programmed reduction of H_2 ($\text{H}_2\text{-TPR}$), temperature-programmed desorption of O_2 ($\text{O}_2\text{-TPD}$), and oxygen pulse chemisorption techniques were used to characterize the structure and redox properties of the perovskites. The relationship between the physicochemical properties and catalytic activity in N_2O decomposition is discussed.

1 Experimental

1.1 Catalyst preparation

Zr-substituted cobalt-based perovskites were prepared using a combined ethylene diamine tetraacetic acid (EDTA) and citric acid complexing sol-gel method described elsewhere [27]. Metal nitrates (all A.R. grade) were the raw materials for the metal ion source. In a representative preparation example, e.g. for the $\text{LaCoO}_{3-\delta}$ sample, calculated amounts of $\text{La}(\text{NO}_3)_3$ (0.01 mol) and $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ (0.01 mol) were first dissolved in deionized water (100 ml). After stirring for 10 min in a 60 °C water bath, citric acid (0.03 mol) was introduced. A EDTA-NH_3 solution (50 ml, contains 0.02 mol EDTA and 13 ml 14.5 mol/L NH_3) was added. A transparent gel was obtained after 7 h under stirring. In this example, the molar ratio of EDTA acid: citric acid: total metal ion was controlled at 1:1.5:1. By evaporation at 100 °C and calcination at 900 °C for 2 h, the gel was transformed into the final perovskite. The samples were denoted with a general formula of $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ or $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$, where x indicated the mole fraction of Zr.

1.2 Catalyst activity measurement

Activity evaluation for N_2O decomposition was carried out in a fixed-bed flow quartz reactor described in the literatures [4,5,7,9]. Prior to the reaction, 100 mg (20–40 mesh) of a catalyst sample were purged with Ar at room temperature for 15 min. Then, the gas flow was switched to the reactant gas containing 30 vol% N_2O in Ar with a flow rate of 50 ml/min (STP), corresponding to a gas hour space velocity (GHSV) of 30000 ml/(h·g). The catalyst temperature was measured using a thermocouple situated close to the catalyst sample. In view of the exothermic nature of N_2O decomposition, each reaction temperature was held for

0.5 h to ensure that both the reaction and thermal environment reached steady state. The effluent gas was analyzed online by an Agilent 6890N gas chromatograph equipped with a Molecular Sieve 13X column and a Porapak Q column. N_2O conversion was determined based on the difference between its inlet and outlet concentrations.

1.3 Physicochemical characterization

BET surface areas of the catalysts were calculated from N_2 adsorption at -196°C using a Micromeritics ASAP 2010 apparatus. The XRD patterns were recorded with a PANalytical X'Pert-Pro powder X-ray diffractometer using $\text{Cu } K_\alpha$ Ni-filtered radiation, $K_{\alpha 1} \lambda = 0.154056 \text{ nm}$ and $K_{\alpha 2} \lambda = 0.154439 \text{ nm}$ at a scan speed of $5^\circ/\text{min}$.

H_2 -TPR profiles were measured on a Micromeritics Autochem 2920 apparatus. A sample (100 mg) was loaded into a U-shape quartz reactor and pretreated in a flow of Ar at 400°C for 1 h. After cooling to 50°C in Ar, the feed gas was switched to a 10% H_2 -90% Ar mixture. Then, the sample was heated to 900°C at a ramp rate of $10^\circ\text{C}/\text{min}$. A thermal conductivity detector (TCD) was used online for measuring H_2 consumption.

O_2 -TPD profiles were also performed on the Micromeritics Autochem 2920 apparatus. The sample (100 mg for each measurement) was pretreated similarly to that for the H_2 -TPR, except that the flow was pure oxygen instead of Ar. After cooling, the sample was flushed with He and then heated to 900°C with the same ramp rate of $10^\circ\text{C}/\text{min}$. Desorbed O_2 was measured with the TCD and was identified with a mass spectrometer.

Oxygen adsorption property was examined with a pulse adsorption method at the reaction temperature. This characterization was similar to that for oxygen storage capacity (OSC) described in the literatures [30,31]. The catalyst (200 mg) was placed in a U-shaped microreactor in the same system as used for H_2 -TPR and O_2 -TPD. The catalyst was pretreated for 5 min in He at 400°C , and then a fixed volume of $5.3900 \text{ cm}^3 \text{ O}_2/\text{He}$ (STP, 2.00 vol% O_2) was introduced by the pulse injection valve at the same temperature. The amount of oxygen in the exhaust was then analyzed online with a TCD detector.

2 Results and discussion

2.1 Catalytic activity

Figure 1 compares the N_2O conversion as a function of reaction temperature over the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites. Pure $\text{LaCoO}_{3-\delta}$ had only slight activity to decompose N_2O in the tested temperature range, with a maximum N_2O conversion of 24% at 700°C . When Zr

Fig. 1. N_2O conversions with $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (a) and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (b).

was introduced, a large improvement was observed. $\text{LaZr}_{0.05}\text{Co}_{0.95}\text{O}_{3-\delta}$, with the least amount of Zr used gave the highest N_2O conversion. When the Zr content was further increased, the catalytic activity decreased but still far exceeded that of $\text{LaCoO}_{3-\delta}$. As for the Ba-based perovskites, $\text{BaCoO}_{3-\delta}$ showed a surprisingly higher activity than $\text{LaCoO}_{3-\delta}$ as illustrated in Fig. 1(b). This is somewhat contrary to the general understanding that Ba in site A of a perovskite is seldom used as a catalyst. Obvious promotion was also obtained when Zr was incorporated. With the increase of Zr content, the activity was first enhanced, and then fell slowly, but the N_2O conversion curve was still shifted to a lower temperature of at least 50°C in comparison with that of $\text{BaCoO}_{3-\delta}$. On the whole, the introduction of Zr into $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites played an important role in improving the catalytic activity for high concentration N_2O decomposition.

2.2 Catalyst characterization results

2.2.1 BET surface area

The specific surface areas of the perovskites are listed in Table 1. $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ had low surface areas because of the high temperature calcination at 900°C . Increases in the BET surface area were observed with both

Table 1 Properties of the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites

Catalyst	x	BET surface area (m^2/g)	Crystalline phase	Crystal system*	La(Ba)CoO_3		$\text{La}_2\text{Zr}_2\text{O}_7(\text{BaZrO}_3)$	$\text{BaCoO}_{2.6}$	
					$a = b$ (nm)	c (nm)	$a = b = c$ (nm)	$a = b$ (nm)	c (nm)
$\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$	0	4.7	LaCoO_3	R	0.5420	1.2999	—	—	—
	0.05	9.3	$\text{LaCoO}_3/\text{La}_2\text{Zr}_2\text{O}_7$	R+C	0.5424	1.3046	1.0793	—	—
	0.3	8.0	$\text{LaCoO}_3/\text{La}_2\text{Zr}_2\text{O}_7$	R+C	0.5419	1.3147	1.0777	—	—
	0.5	7.7	$\text{LaCoO}_3/\text{La}_2\text{Zr}_2\text{O}_7$	R+C	0.5390	1.3162	1.0778	—	—
$\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$	0	0.9	$\text{BaCoO}_3/\text{BaCoO}_{2.6}$	H+H	0.5671	0.4712	—	0.5659	2.8379
	0.05	5.3	$\text{BaCoO}_3/\text{BaCoO}_{2.6}/\text{BaZrO}_3$	H+H+C	0.5634	0.4730	0.4114	0.5659	2.8255
	0.2	9.8	$\text{BaCoO}_3/\text{BaZrO}_3$	H+C	0.5621	0.4747	0.4147	—	—
	0.3	12.2	$\text{BaCoO}_3/\text{BaZrO}_3$	H+C	0.5628	0.4721	0.4146	—	—

*H: Hexagonal; C: Cubic; R: Rhombohedral.

types when Zr was incorporated. $\text{LaZr}_{0.05}\text{Co}_{0.95}\text{O}_{3-\delta}$ and $\text{BaZr}_{0.3}\text{Co}_{0.7}\text{O}_{3-\delta}$ displayed the highest specific surface areas with the values of 9.3 and $12.2 \text{ m}^2/\text{g}$, respectively. The increase in surface area may be due to defects induced by the introducing of Zr and from the change in crystallite size: for the La series, the $\text{La}_2\text{Zr}_2\text{O}_7$ phase did not display the $K_{\alpha 1}$ - $K_{\alpha 2}$ line separation as was the case for the initial LaCoO_3 phase, which meant smaller crystallite sizes (see XRD results). The same result was obtained with the Ba series. This surface area increase and the appearance of new Zr-based phases can explain the activity enhancement in N_2O conversion.

2.2.2 XRD

XRD patterns of the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites are illustrated in Fig. 2. Their crystal structures and lattice parameters are summarized in Table 1. The comparison of the experimental diffractograms with JCPDS charts indicated that all the samples were perovskite phases. Pure $\text{LaCoO}_{3-\delta}$ perovskite presented only the LaCoO_3 phase (JCPDS 00-048-0123) with the rhombohedral symmetry as displayed in Fig. 2(a). When Zr was introduced, the cubic $\text{La}_2\text{Zr}_2\text{O}_7$ phase (JCPDS 00-017-0450) was detected and this became the main phase with $x > 0.3$. The unit cell parameters were close to the values given in the reference files, which meant that there was very limited substitution. Nevertheless, a slight increase of the c parameter can suggest a deformation of the perovskite. It has been reported that it is difficult to substitute in a large amount the B-site cation with a non variable oxidation state (e.g. Mg^{2+} , Al^{3+} , Zr^{4+}) in the perovskite framework [32]. The above results agreed with this.

Analogous results were observed with $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ as shown in Fig. 2(b). $\text{BaCoO}_{3-\delta}$ was a typical hexagonal perovskite with the crystal structure of BaCoO_3 and $\text{BaCoO}_{2.6}$ (JCPDS 00-052-1612 and 01-071-2453, respectively). With the incorporation of Zr, the diffraction peak at $2\theta = 28.46^\circ$ corresponding to $\text{BaCoO}_{2.6}$ decreased to zero. Simultaneously, well crystallized cubic BaZrO_3 (JCPDS

00-006-0399) emerged even for the sample containing the least amount of Zr (0.05). The cell parameters also changed as listed in Table 1. These results again indicated that the incorporation of Zr resulted in the deformation of the framework, especially for the $\text{BaZr}_{0.2}\text{Co}_{0.8}\text{O}_{3-\delta}$ sample.

When the B ion was partially substituted with an ion with a different oxidation state, e.g., $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$, charge compensation is required to achieve electroneutrality. This can be fulfilled either by the formation of oxygen defects or by a valence change of the B metal. In addition, according to above discussion, two or three phases existed in all the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ samples, which can form new interfaces. This also favored the modi-

Fig. 2. XRD patterns of the catalysts $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (a) and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (b).

fication of oxygen defects (mainly oxygen vacancies). The effect of oxygen defects was of crucial importance in N_2O decomposition, and will be further discussed in the following section.

2.2.3 H_2 -TPR

The reducibility of the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites was investigated by H_2 -TPR. Two H_2 consumption ranges were present in the profiles, showing that there was a two-step reduction process as described in the literatures [33,34]. The reduction at temperatures below 500°C was ascribed to the reduction of Co^{3+} to Co^{2+} , and the reduction at higher temperatures was attributed to the complete reduction of Co^{2+} to metallic Co^0 species. As shown in Fig. 3(a), with the introduction of Zr, in $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ the reduction peaks were shifted toward lower temperature, and the peak at low temperature was enlarged while that at high temperature got smaller. In particular, at $x = 0.05$, the sample had the largest reduction peak at the lowest temperature in the series. In order to clearly characterize the state of Co, the H/Co ratio was calculated based on the H_2 consumption. These values are labeled in the figure (supposing Zr^{4+} was not reduced). The estimated standard deviation was 0.1. For the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ samples, the final H/Co ratios were 2.6 or 2.5, which were slightly lower than 3, the nominal H/Co

ratio corresponding to complete reduction of Co^{3+} into metallic Co species. This indicated an incomplete oxidation of the catalyst during the thermal treatment, in agreement with the literature [20]. Strikingly, the H/Co ratio of the first reduction step increased with the incorporation of Zr, implying that more than one electron was involved in the reducing process at low temperature but not at high temperature. It has been discussed with the XRD characterization that the insertion of Zr into $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ can readily lead to lattice deformation due to the different cation radius and valence state. As a consequence, the interaction between Co and O would be changed. From the activity results, it can be seen that the reducibility was closely correlated with the N_2O conversion. The more easily reduced samples gave higher N_2O conversions. Therefore, the facile reduction of the perovskites played a key role in the decomposition of N_2O . This had been used as a sign of high intrinsic oxygen reactivity in cobaltite catalysts for diesel soot combustion [35].

The $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ series also showed a two-step reduction as shown in Fig. 3(b). Different from $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$, the reduction at low temperature was more promoted as seen from the H_2 -TPR profiles and the H/Co ratios. This can be linked to the presence of Co^{3+} in the $\text{BaCoO}_{3-\delta}$ phase. With the incorporation of Zr, the promotion was enhanced until the second reduction step disappeared and was merged into the first step. By reference to the activity results, the facile reduction at low temperature showed the same correlation with activity enhancement, again showing the importance of the reducibility of the perovskites on N_2O decomposition.

2.2.4 O_2 -TPD

It is widely accepted that the decomposition of N_2O proceeds by an oxidation-reduction mechanism [15]. The desorption of oxygen is the rate determining step over various metal oxide catalysts. In view of this, the oxygen desorption behavior were characterized by O_2 -TPD experiments.

As depicted in Fig. 4(a), two desorption peaks were observed with the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ samples. The first peak appearing below 600°C was designated as $\alpha\text{-O}_2$ or suprafacial O_2 desorption, which was related to the oxygen species bound to surface anion vacancies of the perovskite. The other peak detected above 700°C was ascribed to $\beta\text{-O}_2$ or intrafacial O_2 , which was due oxygen species liberated from the lattice [30,33]. Pure $\text{LaCoO}_{3-\delta}$ had an undetectable $\alpha\text{-O}_2$ desorption and an intense $\beta\text{-O}_2$ desorption. With the introduction of Zr, the desorption of $\alpha\text{-O}_2$ was enhanced and that of $\beta\text{-O}_2$ was weakened. At the same time, the two desorption peaks both shifted toward lower temperatures. Among the $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ samples, $\text{LaZr}_{0.05}\text{Co}_{0.95}\text{O}_{3-\delta}$ showed the largest shift. It has been discussed previously that oxygen de-

Fig. 3. H_2 -TPR profiles of the catalysts $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (a) and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ (b).

Fig. 4. O_2 -TPD profiles of the catalysts $LaZr_xCo_{1-x}O_{3-\delta}$ (a) and $BaZr_xCo_{1-x}O_{3-\delta}$ (b).

sorption from the catalyst surface is the rate determining step in N_2O decomposition. Therefore, the facile desorption of oxygen was another reason for the activity enhancement of N_2O decomposition.

In contrast to $LaZr_xCo_{1-x}O_{3-\delta}$, two distinct types of desorption were detected with the $BaZr_xCo_{1-x}O_{3-\delta}$ samples as shown in Fig. 4(b). The α - O_2 desorption was markedly increased when Zr was introduced, which can be induced by the sol-gel preparation method as reported by Dacquin et al. [33]. β - O_2 desorption was also promoted with the Zr content. A new desorption peak at a lower temperature of 300 °C appeared, especially with $BaZr_{0.2}Co_{0.8}O_{3-\delta}$ and $BaZr_{0.3}Co_{0.7}O_{3-\delta}$. The large O_2 desorption, especially α - O_2 desorption, was responsible for the high activity of the Ba based perovskites due to Zr introduction into the $BaZr_xCo_{1-x}O_{3-\delta}$ perovskites.

Generally, O_2 desorption from the lattice of perovskites is associated with B-site ion reduction and anion vacancy generation [23]. It has been confirmed in the H_2 -TPR data that the reduction of the cobalt species was significantly improved in Zr substituted perovskites. This indicated the high intrinsic redox activity of Co-based perovskites substituted with Zr. Hence, the desorption of O_2 species can occur by the weakly linked or chemisorbed oxygen in the lattice of $LaZr_xCo_{1-x}O_{3-\delta}$ and $BaZr_xCo_{1-x}O_{3-\delta}$. It has been mentioned previously that oxygen desorption from the catalyst surface

is the rate determining step for N_2O decomposition. Therefore, the facile desorption of oxygen, especially α - O_2 , was the reason for the activity enhancement of N_2O decomposition.

2.2.5 Oxygen pulse adsorption

The OSC method has been extensively used to study the stability of three way catalysts. This is based on the pulse injection of a small amount of gas (CO or O_2) at regular time intervals [31,36]. It was also proposed as a means to evaluate the surface and bulk oxygen activity of Sr- and Ce-substituted perovskites ($La_{1-x}(Sr,Ce)_xMnO_3$) [37]. In this work, oxygen pulse adsorption was used to detect the adsorption of oxygen on the $LaZr_xCo_{1-x}O_{3-\delta}$ and $BaZr_xCo_{1-x}O_{3-\delta}$ perovskites at the reaction temperature. The results recorded at 400 °C on the sample pretreated in He are shown as an example in Fig. 5. It can be noticed in Fig. 5(a) that both $LaZr_{0.05}Co_{0.95}O_{3-\delta}$ and $LaCoO_{3-\delta}$ samples showed a descending oxygen adsorption amount with pulse number. In contrast, $LaZr_{0.05}Co_{0.95}O_{3-\delta}$ adsorbed more oxygen than these perovskites, especially in the first two pulses. On account of the high test temperature of 400 °C, the oxygen adsorption here was considered to be related to chemisorbed oxygen on vacancies and active oxygen sites. Therefore, the larger oxygen adsorption amount of $LaZr_{0.05}Co_{0.95}O_{3-\delta}$ indicated more oxygen adsorption capability or more oxygen vacancies, which was consistent with the O_2 desorption result in O_2 -TPD. It has been discussed previously that oxygen va-

Fig. 5. Histograms of O_2 pulse adsorption quantity on the catalysts $LaZr_xCo_{1-x}O_{3-\delta}$ (a) and $BaZr_xCo_{1-x}O_{3-\delta}$ (b) in O_2 pulse chemisorptions measurement.

cancies or O_2 desorption favored the N_2O decomposition process. Thus the excellent adsorption property of $\text{LaZr}_{0.05}\text{Co}_{0.95}\text{O}_{3-\delta}$ due to Zr substitution also explained the high catalytic activity for N_2O decomposition.

The pulse oxygen adsorption amount on the $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites in Fig. 5(b) showed the same trend with pulse number as $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$, and $\text{BaZr}_{0.2}\text{Co}_{0.8}\text{O}_{3-\delta}$ adsorbed more oxygen than $\text{BaCoO}_{3-\delta}$. With more careful observation, it can also be found that the $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites had more oxygen adsorption capacity than $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$. These results again verified the important role of Zr substitution.

3 Conclusions

Zr-substituted $\text{La}(\text{Ba})\text{Zr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ perovskites were tested for the catalytic decomposition of high concentrations of N_2O for propellant applications. The introduction of Zr significantly improved the catalytic activity of the perovskites by increasing the surface area and by creating oxygen defects or vacancies. Lattice deformation as well as partial incorporation were detected with the perovskites, especially with $x = 0.05$ and 0.2 for $\text{LaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$ and $\text{BaZr}_x\text{Co}_{1-x}\text{O}_{3-\delta}$, respectively. Further investigations with O_2 -TPD and oxygen pulse adsorption indicated that oxygen desorption-adsorption activity was also promoted by the introduction of Zr. This was another reason for the activity enhancement.

References

- Balcon S, Mary S, Kappenstein C, Gengembre E. *Appl Catal A*, 2000, **196**: 179
- Wallbank J R, Sermon P A, Baker A M, Courtney L, Sambrook R M. The 2nd International Conference on Green Propellants for Space Propulsion. Italy, 2004
- Zakirov V, Sweeting M, Lawrence T, Sellers J. *Acta Astronaut*, 2001, **48**: 353
- Zhao X Y, Cong Y, Lü F, Li L, Wang X D, Zhang T. *Chem Commun*, 2010, **46**: 3028
- Zhu S M, Wang X D, Wang A Q, Cong Y, Zhang T. *Chem Commun*, 2007: 1695
- Zhao X Y, Cong Y, Huang Y Q, Liu S, Wang X D, Zhang T. *Catal Lett*, 2011, **141**: 128
- Liu S, Cong Y, Huang Y Q, Zhao X Y, Zhang T. *Catal Today*, 2011, **175**: 264
- Zhu S M, Wang X D, Wang A Q, Zhang T. *Catal Today*, 2008, **131**: 339
- Tian M, Wang A, Wang X, Zhu Y, Zhang T. *Appl Catal B*, 2009, **92**: 437
- Perez-Ramirez J, Santiago M. *Chem Commun*, 2007: 619
- Alifanti M, Kirchnerova J, Delmon B, Klvana D. *Appl Catal A*, 2004, **262**: 167
- Buchneva O, Rossetti I, Biffi C, Allietta M, Kryukov A, Lebedeva N. *Appl Catal A*, 2009, **370**: 24
- Pena M A, Fierro J L G. *Chem Rev*, 2001, **101**: 1981
- Ishihara T, Kilner J A, Honda M, Sakai N, Yokokawa H, Takita Y. *Solid State Ionics*, 1998, **113–115**: 593
- Kapteijn F, Rodriguez-Mirasol J, Moulijn J A. *Appl Catal B*, 1996, **9**: 25
- Russo N, Mescia D, Fino D, Saracco G, Specchia V. *Ind Eng Chem Res*, 2007, **46**: 4226
- Hueso J L, Holgado J P, Pereniguez R, Mun S, Salmeron M, Caballero A. *J Solid State Chem*, 2010, **183**: 27
- Gunasekaran N, Rajadurai S, Carberry J J. *Catal Lett*, 1995, **35**: 373
- 代小平, 余长春, 吴琼. 催化学报 (Dai X P, Yu Ch Ch, Wu Q. *Chin J Catal*), 2008, **29**: 954
- Dacquin J P, Dujardin C, Granger P. *J Catal*, 2008, **253**: 37
- Dacquin J P, Dujardin C, Granger P. *Catal Today*, 2008, **137**: 390
- Yao W, Wang R, Yang X. *Catal Lett*, 2009, **130**: 613
- Zhang R, Villanueva A, Alamdari H, Kaliaguine S. *J Mol Catal A*, 2006, **258**: 22
- Wang H, Zhao Z, Liang P, Xu C, Duan A, Jiang G, Xu J, Liu J. *Catal Lett*, 2008, **124**: 91
- Dai H, He H, Li P, Gao L, Au C T. *Catal Today*, 2004, **90**: 231
- 马飞, 储伟, 黄利宏, 余晓鹏, 吴永永. 催化学报 (Ma F, Chu W, Huang L, Yu X, Wu Y. *Chin J Catal*), 2011, **32**: 970
- Shao Z P, Yang W S, Cong Y, Dong H, Tong J H, Xiong G X. *J Membr Sci*, 2000, **172**: 177
- Yang W S, Wang H H, Zhu X F, Lin L W. *Top Catal*, 2005, **35**: 155
- Doggali P, Kusaba S, Teraoka Y, Chankapure P, Rayalu S, Labhsetwar N. *Catal Commun*, 2010, **11**: 665
- Levasseur B, Kaliaguine S. *Appl Catal B*, 2009, **88**: 305
- Holmgren A, Andersson B, Duprez D. *Appl Catal B*, 1999, **22**: 215
- Zhu J, Thomas A. *Appl Catal B*, 2009, **92**: 225
- Dacquin J P, Lancelot C, Dujardin C, Da Costa P, Djega-Mariadassou G, Beaunier P, Kaliaguine S, Vaudreuil S, Royer S, Granger P. *Appl Catal B*, 2009, **91**: 596
- Navarro R M, Alvarez-Galvan M C, Villoria J A, González-Jiménez I D, Rosa F, Fierro J L G. *Appl Catal B*, 2007, **73**: 247
- Russo N, Furfori S, Fino D, Saracco G, Specchia V. *Appl Catal B*, 2008, **83**: 85
- Yao H C, Yao Y F Y. *J Catal*, 1984, **86**: 254
- Royer S, Alamdari H, Duprez D, Kaliaguine S. *Appl Catal B*, 2005, **58**: 273