available at www.sciencedirect.com

journal homepage: www.elsevier.com/locate/chnjc

Communication

Direct oxidation of the C_{sp3}–H bonds of N-heterocyclic compounds to give the corresponding ketones using a reusable heterogeneous MnO_x-N@C catalyst

Lanhui Ren ^{a,b}, Lianyue Wang ^b, Ying Lü ^b, Guosong Li ^b, Shuang Gao ^{b,*}^a College of Chemistry, Dalian University of Technology, Dalian 116024, Liaoning, China^b Dalian National Laboratory for Clean Energy, Dalian Institute of Chemical Physics, Chinese Academy of Sciences, Dalian 116023, Liaoning, China

ARTICLE INFO

Article history:

Received 3 June 2016

Accepted 22 June 2016

Published 5 August 2016

Keywords:

Oxidation

Heterogeneous catalyst

Ketone

C–H bond

Manganese

ABSTRACT

Novel reusable MnO_x-N@C catalyst has been developed for the direct oxidation of N-heterocycles under solvent-free conditions using TBHP as benign oxidant to give the corresponding N-heterocyclic ketones. The catalytic system exhibited a broad substrate scope and excellent regioselectivity, as well as being amenable to gram-scale synthesis. This MnO_x-N@C catalyst also showed good reusability and was successfully recycled six times without any significant loss of activity.

© 2016, Dalian Institute of Chemical Physics, Chinese Academy of Sciences.

Published by Elsevier B.V. All rights reserved.

The direct oxidation of the C_{sp3}–H bonds is one of the most important and effective transformations in organic chemistry for the formation of ketones, which are useful intermediates in the synthesis of pharmaceuticals, agrochemicals and natural products [1–10]. N-Heterocycles are ubiquitous in natural products and pharmaceutical compounds, which exhibit a broad range of biological and medically relevant activities. Furthermore, a large number of pharmaceutical compounds have been derived from N-heterocyclic ketones, such as arpromidine, pheniramine, chlorpheniramine, triprolidine and doxylamine [11]. Traditionally, N-heterocyclic ketones have been synthesized using stoichiometric quantities of hazardous oxidant, resulting in the production of large amounts of unwanted byproducts [12–14]. During the last few decades, there have been numerous improvements in the methods available

for the oxidation of N-heterocycles to give the corresponding N-heterocyclic ketones using transition metal catalysts [11,15–23]. However, the coordination of N-heterocyclic compounds to transition metals can result in the deactivation of the catalyst and poor chemoselectivity, and the purification of the resulting products can be complicated by difficulties associated with the removal of the metal residues. To address these issues, several researchers have focused on the development of non-metal catalysts during the last decade to affect these oxidative transformations [24,25]. Several activators have also been developed to improve the reactivity of aliphatic methylene groups, such as ethyl chloroacetate [22] and Brønsted acids [25].

Although many strategies have been developed for the oxidation of N-heterocycles to give the corresponding N-heterocy-

* Corresponding author. Tel: +86-411-84379248; E-mail: sgao@dicp.ac.cn

This work was supported by the National Basic research Program of China (973 Program, 2009CB623505) and the National Natural Science Foundation of China (21273225).

DOI: 10.1016/S1872-2067(16)62503-2 | http://www.sciencedirect.com/science/journal/18722067 | Chin. J. Catal., Vol. 37, No. 8, August 2016

clic ketones, most catalysts reported to date for these oxidative transformations are homogeneous. These catalysts are therefore difficult to recycle and often require high reaction temperatures, which has further limited their scope and application. The development of economically and environmentally friendly alternatives to these existing procedures is therefore strongly desired. Heterogeneous catalysts are preferred to homogenous systems because they can be readily recovered and reused. In 2012, Akhlaghinia et al. [26] reported the oxidation of 2-benzylpyridine to 2-benzoylpyridine using ceria nanoparticles as a catalyst. Unfortunately, this reaction used KBrO_3 as an oxidant, which is highly toxic, making it harmful to human health and the environment. This catalyst system also required the use of an organic solvent, making it environmentally unfriendly. Herein, we reported the development of a novel, reusable $\text{MnO}_x\text{-N@C}$ catalyst for the direct oxidative transformations of $\text{C}_{\text{sp}^3}\text{-H}$ bonds to ketones using TBHP as an oxidant. Notably, this $\text{MnO}_x\text{-N@C}$ catalyst is inexpensive with several notably advantages over existing systems, including a low loading, good functional group tolerance, high selectivity and good reusability. Most notably, this new $\text{MnO}_x\text{-N@C}$ catalyst can be used under solvent-free conditions at lower reaction temperatures (Fig. 1).

The results of our previous work showed that 2,3-cyclopentenopyridine may be oxidized to 6,7-dihydro-5H-cyclopenta[b]pyridin-5-one using $\text{Mn}(\text{OTf})_2$ as a catalyst [23]. However, this particular catalyst system was difficult to recycle and expensive, thereby limiting its potential for industrial applications. Furthermore, this oxidation reaction required a large excess of TBHP (5 equiv.). To address these issues, we developed a new $\text{MnO}_x\text{-N@C}$ catalyst, which is highly reusable and requires a much smaller amount of TBHP (3 equiv.). We chose $\text{Mn}(\text{NO}_3)_2$ as the metal source because nitryl is a good electron-withdrawing anion, just like trifluoromethanesulfonate, and $\text{Mn}(\text{NO}_3)_2$ is commercially inexpensive. The $\text{MnO}_x\text{-N@C}$ catalysts were prepared by the complexation of $\text{Mn}(\text{NO}_3)_2$ with 1,10-phenanthroline, followed by pyrolysis at a high temperature (400–900 °C) for 2 h under an atmosphere of nitrogen (Scheme 1). First, the pyrolysis characteristics of complex **A** from $\text{Mn}(\text{NO}_3)_2$ and 1,10-phenanthroline were studied under an atmosphere of nitrogen by thermogravimetric analysis (Fig. 2). The result of this analysis showed that the weight of the complex remained stable for temperatures in the range of 400–600 °C. Furthermore, the carbonization of the complex occurred in this temperature range. However, the mass of the complex rapidly decreased by 53.99% when the temperature reached 365 °C. This change was attributed to the decomposition of the complex with the loss of 1,10-phenanthroline, which

Scheme 1. Preparation of the $\text{MnO}_x\text{-N@C}$ catalysts.

would have evaporation (the boiling point of 1,10-phenanthroline is 365 °C at 1 atm). The carbide gradually decomposed at temperatures over 600 °C. Taken together, the results of this analysis revealed that 600 °C was the most appropriate temperature for the preparation of the $\text{MnO}_x\text{-N@C}$ catalyst.

A 50 mL round-bottom flask (RBF) was charged with $\text{Mn}(\text{NO}_3)_2$ (2.3 g, 6.4 mmol, 50% in water), 1,10-phenanthroline (2.3 g, 12.8 mmol) and EtOH (40 mL). The flask was then sealed, and the mixture was stirred at 80 °C for 12 h. The reaction mixture was cooled to room temperature and filtered through a pad of Celite. The filter cake was subsequently collected and dried at 120 °C for 2 h to give complex **A** in 93% yield.

Complex **A** (3.3 g) was subsequently pyrolyzed at 500 °C under an atmosphere of nitrogen for 2 h to give the $\text{MnO}_x\text{-N@C}$ -catalyst (pyrolysis at 500 °C) in 32% yield.

Several other $\text{MnO}_x\text{-N@C}$ -catalysts (pyrolyzed at 400, 600, 700, 800 and 900 °C) were also prepared according to this general oxidation procedure.

A 15-mL RBF was charged with substrate (0.5 mmol), $\text{MnO}_x\text{-N@C}$ catalyst (1 mg, pyrolysis at 600 °C) and TBHP (1.5 mmol, 65% in H_2O). The flask was then sealed, and the mixture was heated at 60 °C for 12 h. The reaction was cooled to room temperature and diluted with ethyl acetate (4 mL), before being centrifuged at 10000 r/min for 1 min to separate the catalyst. The supernatant was removed and the catalyst was washed with ethyl acetate (5×4 mL). The supernatant was subsequently combined the ethyl acetate wash solutions and evaporated to dryness to give a residue, which was purified by flash column chromatography over silica gel (ethyl acetate/*n*-hexane = 1:10, v/v).

The oxidation of 2-benzylpyridine to give 2-benzoylpyridine (**2a**) was selected as a model reaction to study the catalytic activity of new $\text{MnO}_x\text{-N@C}$ materials. It is noteworthy that all of

Fig. 1. Direct oxidation of the $\text{C}_{\text{sp}^3}\text{-H}$ bonds of N-heterocyclic systems using a reusable heterogeneous $\text{MnO}_x\text{-N@C}$ catalyst.

Fig. 2. The thermogravimetric analysis of the complex **A** from $\text{Mn}(\text{NO}_3)_2$ and 1,10-phenanthroline.

these experiments were conducted under solvent-free conditions. As expected, the $\text{MnO}_x\text{-N@C}$ material (pyrolysis at 600 °C) showed the highest catalytic activity for the direct oxidation of 2-benzylpyridine, affording 2-benzoylpyridine in 82% yield (Table 1, entries 1–6). 2-Benzoylpyridine (**2a**) was obtained in 13% yield when the reaction was conducted in the absence of the catalyst (Table 1, entry 7). Furthermore, none of the desired 2-benzoylpyridine (**2a**) product was detected when O_2 or H_2O_2 was used as the oxidant (Table 1, entries 8 and 9). We also investigated different loadings of the $\text{MnO}_x\text{-N@C}$ -catalyst (pyrolysis at 600 °C). The results revealed that the use of 1 mg of $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C) gave 2-benzoylpyridine (**2a**) in 95% yield, indicating that the adsorption of 2-benzoylpyridine (**2a**) onto the $\text{MnO}_x\text{-N@C}$ material may result in a lower yield (Table 1, entries 10–17). ICP experiments demonstrated that the percentage of Mn in the catalyst was 21.72%, representing a mole fraction of only 0.79 mol%. This result therefore indicated that the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C) has a very high catalytic activity. To the best of our knowledge, this study represents the first reported account of the use of a $\text{MnO}_x\text{-N@C}$ catalyst for the efficient oxidation of an organic substrate under mild conditions. The reaction temperature and different amounts of TBHP were also studied (Table 1, entries 18–23), and the results revealed that the optimum reaction temperature and amount of TBHP were 60 °C and 3 equiv., respectively, producing 2-benzoylpyridine (**2a**) in 91% yield (Table 1, entry 21). Several attempts were made to reduce the reaction time, but resulted in much lower yield (Table 1, entry 24).

The $\text{MnO}_x\text{-N@C}$ material (pyrolysis at 600 °C) was initially characterized by transmission electron microscopy (TEM) and X-ray photoelectron spectroscopy (XPS). The TEM images revealed that the MnO_x particles were about 1.71–6.56 nm in size (Fig. 3(a) and (b)). The peaks in the N 1s spectrum at 398.3 and

Table 1

The oxidation of the $\text{C}_{sp^3}\text{-H}$ bonds of 2-benzylpyridine under various conditions.

Entry	Pyrolysis (°C)	Dosage (mg)	Oxidant	Temperature (°C)	Yield ^a (%)
1	400	25	TBHP, 5 equiv.	80	36
2	500	25	TBHP, 5 equiv.	80	68
3	600	25	TBHP, 5 equiv.	80	82
4	700	25	TBHP, 5 equiv.	80	81
5	800	25	TBHP, 5 equiv.	80	72
6	900	25	TBHP, 5 equiv.	80	76
7	—	—	TBHP, 5 equiv.	80	13
8	600	25	O_2 , 3 atm	80	Nr
9	600	25	H_2O_2 , 5 equiv.	80	Nr
10	600	35	TBHP, 5 equiv.	80	80
11	600	30	TBHP, 5 equiv.	80	81
12	600	20	TBHP, 5 equiv.	80	82
13	600	15	TBHP, 5 equiv.	80	82
14	600	10	TBHP, 5 equiv.	80	85
15	600	5	TBHP, 5 equiv.	80	86
16	600	3	TBHP, 5 equiv.	80	95
17	600	1	TBHP, 5 equiv.	80	95
18	600	1	TBHP, 3 equiv.	80	93
19	600	1	TBHP, 2 equiv.	80	89
20	600	1	TBHP, 3 equiv.	70	90
21	600	1	TBHP, 3 equiv.	60	91
22	600	1	TBHP, 3 equiv.	50	84
23	600	1	TBHP, 3 equiv.	40	59
24 ^b	600	1	TBHP, 3 equiv.	60	77

^a GC yield with biphenyl as the internal standard.

^b Reaction time: 6 h.

399.7 eV were assigned to the N atoms in C–N and C=N bonds, respectively. The electron binding energy observed at 400.8 eV is characteristic of pyrrole-type nitrogen atoms, which can be formed following the carbonization of nitrogen-containing or-

Fig. 3. TEM images (a, b) of the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C); N 1s (c) and Mn $2p_{3/2}$ (d) of the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C).

Scheme 2. $\text{MnO}_x\text{-N@C}$ -catalyzed oxidation of substituted 2-benzylpyridines, 4-benzylpyridines and 2-ethylpyrazine. The isolated yields of **2a–2l** were obtained after column chromatography. The yield of **2m** was determined by ^1H NMR spectroscopy.

ganic materials (Fig. 3(c)) [27,28]. Based on the literature, the peaks in the $\text{Mn } 2p_{3/2}$ spectrum at 640.8, 641.0 and 642.0 eV were assigned to Mn(II) , Mn(III) and Mn(IV) , respectively (Fig. 3(d)) [29,30].

Given that the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C) displayed the best activity for the direct oxidation of 2-benzylpyridine to 2-benzoylpyridine (**2a**), we evaluated the scope of this catalyst using a broad range of substrates. As shown in Scheme 2, a series of structurally diverse 2- and 4-benzylpyridines reacted smoothly in the presence of this catalyst system to give good to excellent yields of the corresponding ketones. As well as 2-benzylpyridine substrates bearing electron-donating groups, which improved the reactivity of the C–H bonds of these substituted systems (Scheme 2, **2e–2g**), we also investigated substrates bearing electron-withdrawing groups (e.g., halide and cyano groups, Scheme 2, **2b–2d**, **2h**). Substrates containing two chemically different benzylic positions were also tested, and reacted in a regioselective manner to give the corresponding ketones **2e** and **2l** as single products in good yields (Scheme 2). The selectivity of the $\text{MnO}_x\text{-N@C}$ -catalyst (pyrolysis at 600 °C) was attributed to the nitrogen atom adjacent to the benzylic moiety directing the oxidation to this position by coordinating to the metal. The poorer reactivity of the 4-benzylpyridine substrates compared with the 2-benzylpyridine systems is also consistent

Scheme 3. $\text{MnO}_x\text{-N@C}$ -catalyzed oxidation of 2,3-cyclopentenopyridine analogues. Isolated yield after column chromatography.

with this directing effect (Scheme 2, **2j**, **2k**). 2-Ethylpyrazine was also evaluated as a substrate and gave 2-acetylpyrazine (**2m**) obtained in good yield (Scheme 2). To the best of our knowledge, this work represents the first reported example of the direct oxidation of 2-ethylpyrazine to give 2-acetylpyrazine (**2m**) in good yield. For example, Wolt [31] only reported 1% yield for the same reaction, highlighting the effectiveness of our new catalyst.

6,7-Dihydro-5H-cyclopenta[b]pyridin-5-one (**2n**) is a very important and expensive intermediate in the synthesis of anti-psychotics. With this in mind, we evaluated the direct oxidation of various 2,3-cyclopentenopyridine analogues using this new catalyst system. Pleasingly, we obtained the corresponding ketones in good yields (Scheme 3, **2n–2r**), thereby highlighting the economic potential of our new catalyst system.

To highlight the synthetic utility of our catalyst system, we conducted a gram-scale reaction using 2-(4-chlorobenzyl)pyridine as a test substrate. The desired ketone product **2b** was obtained in 86% isolated yield within 48 h (Scheme 4). This result therefore confirmed that our newly developed $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C) is a highly active catalyst for the preparation of 2-(4-chlorobenzoyl)pyridine (**2b**) under solvent-free conditions.

Six consecutive oxidation experiments were conducted on one gram scale using 2-(4-chlorobenzyl)pyridine as a substrate to demonstrate the stability and reusability of the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C). Notably, this catalyst was successfully recycled up to six times without any significant loss of activity (Fig. 4).

Based on our previous studies [23,25] and pertinent literature [32], a possible mechanism was proposed (Scheme 5).

Scheme 4. Gram-scale reaction with the $\text{MnO}_x\text{-N@C}$ -catalyst (pyrolysis at 600 °C).

Fig. 4. Recycling of the $\text{MnO}_x\text{-N@C}$ catalyst (pyrolysis at 600 °C) for oxidation experiments of 2-(4-chlorobenzyl)pyridine. Reaction conditions: 2-(4-chlorobenzyl)pyridine (5 mmol), TBHP (15 mmol) and catalyst (10 mg, 0.79 mol % Mn) at 60 °C for 48 h. Isolated yield after column chromatography.

First, the decomposition of *t*-BuOOH would produce *t*-BuO· and ·OH radicals, which would react with the $\text{MnO}_x\text{-N@C}$ catalyst to give HO-MnO_x-N@C (species **C**). Species **C** would subsequently react with *t*-BuOOH to give the corresponding peroxy-complex **D**. The *t*-BuO· radical generated by the decomposition of *t*-BuOOH would capture a H· radical from *t*-BuOOH to give radical **B**, which would selectively abstract a hydrogen atom from the H-heterocyclic substrate to produce radical **E**. Peroxy-complex **D** would then react with radical **E** to give intermediate **F**, which would decompose to give compound **2a**. The XPS results revealed that the $\text{MnO}_x\text{-N@C}$ catalyst contained Mn in multiple valence states. With this in mind, we concluded that Mn(II) transferred a *t*-BuOO· radical to the carbon-centered radical **E** via manganese peroxide **D**.

In summary, we have reported for the first time the development of a stable, inexpensive and reusable $\text{MnO}_x\text{-N@C}$ catalyst for the direct oxidation of N-heterocycles under solvent-free conditions using TBHP as benign oxidant to give the

Scheme 5. Proposed mechanism for this oxidation reaction.

corresponding N-heterocyclic ketones. This $\text{MnO}_x\text{-N@C}$ catalyst exhibited a wide substrate scope and excellent regioselectivity, as well as being amenable to gram-scale synthesis.

References

- [1] S. E. Allen, R. R. Walvoord, R. Padilla-Salinas, M. C. Kozlowski, *Chem. Rev.*, **2013**, 113, 6234–6458.
- [2] Z. Z. Shi, C. H. Zhang, C. Tang, N. Jiao, *Chem. Soc. Rev.*, **2012**, 41, 3381–3430.
- [3] A. N. Campbell, S. Stahl, *Acc. Chem. Res.*, **2012**, 45, 851–863.
- [4] C. Liu, H. Zhang, W. Shi, A. W. Lei, *Chem. Rev.*, **2011**, 111, 1780–1824.
- [5] T. Punniyamurthy, S. Velusamy, J. Iqbal, *Chem. Rev.*, **2005**, 105, 2329–2364.
- [6] C. L. Sun, B. J. Li, Z. J. Shi, *Chem. Rev.*, **2011**, 111, 1293–1314.
- [7] A. Kleemann, J. Engel, B. Kutscher, D. Reichert, *Pharmaceutical Substances*, 4th ed., Georg Thieme, Stuttgart, **2008**.
- [8] D. C. Reis, M. C. X. Pinto, E. M. Souza-Fagundes, S. M. S. V. Wardell, J. L. Wardell, H. Beraldo, *Eur. J. Med. Chem.*, **2010**, 45, 3904–3910.
- [9] A. C. Guyton, J. E. Hall, *Textbook of Medical Physiology*, 11th ed., Elsevier Saunders, Philadelphia, **2006**.
- [10] J. Easmon, G. Heinisch, G. Pürstinger, T. Langer, J. K. Österreicher, H. H. Grunicke, J. Hofmann, *J. Med. Chem.*, **1997**, 40, 4420–4425.
- [11] B. Pieber, C. O. Kappe, *Green Chem.*, **2013**, 15, 320–324.
- [12] K. E. Crook, S. M. Mceivain, *J. Am. Chem. Soc.*, **1930**, 52, 4006–4011.

Graphical Abstract

Chin. J. Catal., 2016, 37: 1216–1221 doi: 10.1016/S1872-2067(16)62503-2

Direct oxidation of the C_{sp3}-H bonds of N-heterocyclic compounds to give the corresponding ketones using a reusable heterogeneous $\text{MnO}_x\text{-N@C}$ catalyst

Lanhui Ren, Lianyue Wang, Ying Lü, Guosong Li, Shuang Gao *

Dalian University of Technology; Dalian Institute of Chemical Physics, Chinese Academy of Sciences

A novel reusable $\text{MnO}_x\text{-N@C}$ catalyst has been developed for the direct oxidation of N-heterocycles under solvent-free conditions using TBHP as a benign oxidant to give the corresponding N-heterocyclic ketones. This catalytic system exhibited broad substrate scope and excellent regioselectivity, as well as being amenable gram-scale synthesis. Notably, this $\text{MnO}_x\text{-N@C}$ catalyst was successfully recycled six times without any significant loss of activity.

- [13] E. H. Huntress, H. C. Walter, *J. Am. Chem. Soc.*, **1948**, 70, 3702–3707.
- [14] J. Stevens, G. Sumrell, G. Ham, *J. Org. Chem.*, **1957**, 22, 1724–1725.
- [15] M. Itoh, K. Hirano, T. Satoh, M. Miura, *Org. Lett.*, **2014**, 16, 2050–2053.
- [16] J. D. Houwer, T. K. Abbaspour, B. U. W. Maes, *Angew. Chem. Int. Ed.*, **2012**, 51, 2745–2748.
- [17] J. J. Dong, D. Unjaroen, F. Mecozzi, E. C. Harvey, P. Saisaha, D. Pijper, J. W. de Boer, P. Alsters, B. L. Feringa, W. R. Browne, *ChemSusChem*, **2013**, 6, 1774–1778.
- [18] M. Nakanishi, C. Bolm, *Adv. Synth. Catal.*, **2007**, 349, 861–864.
- [19] S. Nawratil, M. Grypioti, C. Menendez, S. Mallet-Ladeira, C. Lherbet, M. Baltas, *Eur. J. Org. Chem.*, **2014**, 2014, 654–659.
- [20] S. F. Hsu, B. Plietker, *ChemCatChem*, **2013**, 5, 126–129.
- [21] A. Citterio, R. Sebastiano, M. C. Carvayal, *J. Org. Chem.*, **1991**, 56, 5335–5341.
- [22] J. M. Liu, X. Zhang, H. Yi, C. Liu, R. Liu, H. Zhang, K. L. Zhuo, A. W. Lei, *Angew. Chem. Int. Ed.*, **2015**, 54, 1261–1265.
- [23] L. H. Ren, L. Y. Wang, Y. Lü, S. S. Shang, B. Chen, S. Gao, *Green Chem.*, **2015**, 17, 2369–2372.
- [24] J. T. Zhang, Z. T. Wang, Y. Wang, C. F. Wan, X. Q. Zheng, Z. Y. Wang, *Green Chem.*, **2009**, 11, 1973–1978.
- [25] L. H. Ren, L. Y. Wang, Y. Lü, G. S. Li, S. Gao, *Org. Lett.*, **2015**, 17, 2078–2081.
- [26] B. Akhlaghinia, H. Ebrahimabadi, E. K. Goharshadi, S. Samiee, S. Rezazadeh, *J. Mol. Catal. A*, **2012**, 357, 67–72.
- [27] X. D. Zhuang, Y. Chen, G. Liu, P. P. Li, C. X. Zhu, E. T. Kang, K. G. Neoh, B. Zhang, J. H. Zhu, Y. X. Li, *Adv. Mater.*, **2010**, 22, 1731–1735.
- [28] R. V. Jagadeesh, H. Junge, M. M. Pohl, J. Radnik, A. Brückner, M. Beller, *J. Am. Chem. Soc.*, **2013**, 135, 10776–10782.
- [29] V. P. Santos, M. F. R. Pereira, J. J. M. Órfão, J. L. Figueiredo, *Appl. Catal. B*, **2010**, 99, 353–363.
- [30] Y. J. Wei, L. Y. Yan, C. Z. Wang, X. G. Xu, F. Wu, G. Chen, *J. Phys. Chem. B*, **2004**, 108, 18547–18551.
- [31] J. Wolt, *J. Org. Chem.*, **1975**, 8, 1178–1179.
- [32] A. J. Catino, R. E. Forslund, M. P. Doyle, *J. Am. Chem. Soc.*, **2004**, 126, 13622–13623.

多相 MnO_x 氮掺杂碳材料催化氮杂环侧链 $\text{C}_{sp^3}\text{-H}$ 的氧化反应

任兰会^{a,b}, 王连月^b, 吕 迎^b, 李国松^b, 高 爽^{b,*}

^a大连理工大学化学学院, 辽宁大连 116024

^b中国科学院大连化学物理研究所洁净能源国家实验室(筹), 辽宁大连 116023

摘要: sp^3 杂化的碳氢键氧化成酮是有机合成中一个重要方法. 相应的酮产物被广泛应用在医药和天然产物合成中. 目前已经开发出多种衍生于含 N 杂环酮的药物化合物和具有生物活性的天然产物, 例如阿普米定、苯吡胺、氯苯吡胺、曲普利啶、多西拉敏等. 传统的含 N 杂环侧链氧化生成酮的方法使用化学计量的强氧化剂 (如高锰酸钾), 不可避免地产生众多的副产物. 近年来, 均相的过渡金属催化剂被广泛应用于含 N 杂环侧链氧化生成酮的反应中. 但是 N 杂环和过渡金属配位导致催化剂失活, 选择性降低. 金属的残留也使后处理过程变得繁琐. 均相催化剂还存在难以回收利用的缺点. 使用多相催化剂可以解决上述问题, 因而具有重大的研究意义. 目前为止, 还很少有文献报道多相催化剂催化含 N 杂环侧链氧化生成酮的方法.

本文使用硝酸锰和菲啉的络合物在氮气氛围中高温焙烧, 制备了一系列新型 $\text{MnO}_x\text{-N@C}$ 材料. 首次应用于 C–H 氧化成酮的领域中. 以 2-苄基吡啶为模板底物, 使用叔丁基过氧化氢为氧化剂, 我们研究了 $\text{MnO}_x\text{-N@C}$ 材料的催化活性. 研究发现, 在 600 °C 焙烧得到的 $\text{MnO}_x\text{-N@C}$ 材料具有最高的催化活性. 实验得到最佳的反应条件: 0.5 mmol 底物, 3 当量的叔丁基过氧化氢, 1 mg $\text{MnO}_x\text{-N@C}$ (600 °C) 材料. ICP 结果表明, 1 mg $\text{MnO}_x\text{-N@C}$ (600 °C) 材料中含有的锰相对于 0.5 mmol 底物的摩尔分数为 0.79 mol%, 说明该材料具有很高的催化活性. 我们进一步研究了 $\text{MnO}_x\text{-N@C}$ (600 °C) 材料适用的底物范围, 发现它可以催化 2,3-环戊烯并吡啶类化合物、苄基吡啶类化合物发生氧化反应生成相应的酮; 当反应底物中存在其他可以被氧化的碳氢键时, 该材料表现出很高的选择性, 可见其具有广泛的底物范围和优异的选择性. 对于克级以上规模的底物量, $\text{MnO}_x\text{-N@C}$ 仍能表现出很高的催化活性, 表明其在有机合成中具有很好的实用性; 连续使用 6 次后, 该催化剂依然表现出很高的催化活性. 表征结果表明, $\text{MnO}_x\text{-N@C}$ (600 °C) 材料中 MnO_x 粒子大小为 1.71–6.56 nm; 样品中存在 C–N, C=N 和吡咯型的 N; Mn 的化学态有 +2, +3 和 +4.

关键词: 氧化; 多相催化剂; 酮; 碳氢键; 锰

收稿日期: 2016-06-03. 接受日期: 2016-06-22. 出版日期: 2016-08-05.

*通讯联系人. 电话: (0411)84379248; 电子信箱: sgao@dicp.ac.cn

基金来源: 国家重点基础研究发展计划 (973 计划, 2009CB623505); 国家自然科学基金 (21273225).

本文的英文电子版由 Elsevier 出版社在 ScienceDirect 上出版 (<http://www.sciencedirect.com/science/journal/18722067>).