available at www.sciencedirect.com

journal homepage: www.elsevier.com/locate/chnjc

Perspective

Recent progress on oxygen and hydrogen peroxide reduction reactions on Pt single crystal electrodes

Valentín Briega-Martos, Enrique Herrero, Juan M. Feliu *

1. Introduction

The oxygen reduction reaction (ORR) is probably the most important cathodic process in electrocatalysis because of its universal role as comburent in life and key applications in several fields such as fuel cells, corrosion processes or lithium-air batteries. Despite many experimental and theoretical investigations that have been carried out during the last years and contributed to improve the knowledge about this reaction, the complete mechanism for the ORR is not elucidated yet [1]. The ORR involves the exchange of 4 electrons and 4 protons for the complete reduction of O_2 to water (Eq. 1). The reaction mechanism is complex and implies the formation of several intermediates involving O=O bond scission and O–H bond formation.

It was demonstrated that H_2O_2 is a reaction intermediate for this reaction under certain conditions [2–4]. H_2O_2 could be the final product in a 2-electron reduction process (Eq. 2), or it could be further reduced to water (Eq. 3).

The study of the hydrogen peroxide reduction and oxidation reactions (HPRR and HPOR) is therefore crucial for a better understanding of the ORR as it is a possible stable intermediate.

Previous theoretical studies taking into account the binding energy of OH intermediate indicated that Pt(111) is the most active surface towards the ORR [5]. However, the analysis of the electrocatalytic activity of the basal planes by extrapolation of experimental data for stepped surfaces pointed out that the stepped surfaces are more active than Pt(111) in acidic media [6–8], while in alkaline media experimental results and theory agree better [9]. This has been a controversial point during all the ORR research. The surface charge of the electrode can also have an influence towards the kinetics of the electrocatalytic reactions, but its specific effect has not been considered until recent works. The study of the ORR in different surface charge conditions can help to overcome the unsolved aspects for this reaction.

Other problems to elucidate the ORR mechanism are the dif-

ficulty for identifying the reaction intermediates. The traditionally available techniques are not able to detect all the reaction intermediates in the ORR [10]. Because of that it is important to compare theoretical calculations with the available experimental results in order to propose the possible intermediates [11,12].

In this perspective paper, the most recent advances in the understanding of the ORR (and the HPRR) on well-oriented Pt surfaces are summarized in order to provide a general vision of what is known to date and the next strategies that could be employed.

2. Effect of the surface charge on the ORR and the HPRR

The adsorption energy of the ORR intermediates is usually the descriptor used in kinetic investigations [5]. However, the electrode surface charge can also have a markedly influence on the electrocatalytic reactions [13]. For the study of the effect of the surface charge on the electrocatalytic activity of Pt electrodes is necessary to use working solutions without the presence of anions that adsorb specifically, since the latter ones can also modify the reactivity of the electrode [7]. The use of NaF/HClO₄ mixtures resulted to be suitable for this type of study at different pH because the pK_a of hydrofluoric acid is ca. 3 and F⁻ does not adsorb specifically on Pt [14]. This kind of electrolyte was used to study the ORR on Pt basal planes and different stepped surfaces in a pH range up to until 5.6 [15]. The cyclic voltammetry results for Pt(111) show that the onset potential moves to slightly more positive values as the solution pH increases (Figure 1A). The kinetic current densities at 0.85 V vs. RHE obtained by using the Koutecky-Levich equation are also improved as the pH is changed from acid to more neutral values (Figure 1D). The reaction was also studied in alkaline pH values from pH 11.9 to 13.1 using NaOH/KClO₄ mixtures, and in this case the higher the pH, the lower the kinetic current densities (Figure 1D). In conclusion, for Pt(111), the plot j_{kin} vs. pH shows a volcano trend with the maximum centered at pH ca. 9. The proposed explanation for this behavior was based on the fact that the potential of zero free charge (pzfc) for Pt(111)

Fig. 1. Polarization curves for the ORR on Pt(111) (A), Pt(100) (B) and Pt(110) (C) in O_2 -saturated solutions with pH < 5.6 prepared with NaF/HClO₄ mixtures. Plot of the logarithm of j_k at 0.85 V on the different Pt single crystal electrodes as a function of pH. The straight lines correspond to Pt(111) (D). Normalized polarization curves for the HPRR and HPOR on Pt(111) in 1.7 mmol/L H_2O_2 with pH < 5.4 prepared with NaF/HClO₄ mixtures in the SHE scale. The dotted line marks the potential at which the first current drops starts for the different pH values (E). Normalized polarization curves for the HPRR and HPOR on different Pt(S)[n(111)×(111)] stepped surfaces in 0.1 mol/L HClO₄ and 1.7 mmol/L H_2O_2 (F). Scan rate: 50 mV/s; rotation rate: 2500 rpm (for all the figures). Figures 1A, 1B, 1C, and 1D are adapted from Ref. [15]. Figure 1E is adapted from Ref. [16].

moves to more positive potentials in the RHE scale as the pH is increased from acidic values to pH = 6. Therefore, the onset potential for the ORR is closer to the pzfc for neutral pH values. The electrocatalytic activity would be maximum when the onset potential is close to the pzfc for the Pt(111) surface. When the pH is increased to alkaline values, the onset potential is gradually more negative than the pzfc, and thus the electrocatalytic activity decreases again. For Pt(100) and Pt(110) the situation is different (Figures 1B and 1C): the j_k values decrease slightly as the pH is increased in the whole potential range. This is because for Pt(111) the onset potential lies at potential values where OH species are adsorbed, but as the potential is swept to more positive values adsorbed OH desorbs at ca. 0.7. In the case of the other basal planes, however, the OH desorption takes place at much more negative values, and therefore at the relevant potential region for the ORR the surface always is covered by OH. The ORR is then mainly affected by the adsorbed OH and this is the reason for the almost constant observed behavior. The situation for the Pt(S)[(n-1)(111)×(110)] and Pt(S)[n(111)×(100)] is intermediate, since it can also be observed a volcano trend but with less pronounced slopes. This is because the fraction of (111) terraces is smaller as the step density is increased and may suggest that the overall reactivity depends on local contributions from terraces and steps. The possible effects of the surface charge on the ORR mechanism are discussed in Sections 4 and

5.

The effect of surface charge was also studied for the HPRR [16]. The inhibition of the current density that takes place at low potentials for the ORR on Pt(111) was traditionally ascribed to the adsorption of hydrogen, which would hinder the scission of the O–O and yielding thus H_2O_2 instead of water [3]. However, measurements with NaF/HClO₄ mixtures at different pH values showed that this inhibition always occurs at the same potential in the SHE scale (Figure 1E) [16]. This potential is very near to the potential of maximum entropy (pme) for Pt(111). Consequently, the inhibition must be related to some change in the interfacial water or to the surface charge of the electrode instead of the proposed hydrogen adsorption. The HPRR was also studied in alkaline media, but in this case the inhibition potential is determined by the OH adsorption/desorption potential [16].

Further studies have been carried out using Pt stepped surfaces (Figure 1F). On one hand, it can be observed that the current density inhibition potential shifts to more positive potential values with step density. This is in agreement with the variation of the local pme for terraces in stepped surfaces measured by laser-induced temperature jump experiments [17]. On the other hand, the intensity for the current density minimum observed at ca. 0.11 V vs. RHE increases as the step density is increased and this potential coincides well with the local pme for steps. In conclusion, there is a clear influence of the local

surface charge properties towards the HPRR.

3. Experimental evidences of a bifurcation point in the ORR mechanism

Since the mechanism for the ORR involves several steps, there can exist bifurcation points from which, depending on the conditions, the reaction can follow different pathways. The $\text{OOH}^\bullet$ species has been proposed previously in several works as a possible bifurcation point which could yield directly adsorbed O and OH or produce H_2O_2 [10]. It can be seen in Figure 1A that the limiting current densities for the ORR on Pt(111) decreases as the solution pH is increased from pH ca. 3. Analogous experiments for HPRR with a H_2O_2 concentration that would lead to the same limiting current densities were performed, but in this case no decrease of j_{lim} was observed (Figure 2A) [15]. It was proposed that this behavior for the ORR is due to the existence of a bifurcation point before the formation of H_2O_2 . This

previous intermediate would stop reacting electrochemically giving rise to a reduction in the faradaic efficiency. This intermediate was suggested to be $\text{OOH}^\bullet$ soluble species in light of the results by Gómez-Marín et al. [15].

The mechanism of the ORR was also studied by investigating the effect of the presence of Br^- in working solutions with different pH values [18]. It was observed that at very acidic pH values (below pH = 1) the presence of Br^- reduces the j_{lim} to the half of its theoretical value. Therefore, the final product in these conditions is H_2O_2 . However, as solution pH increases, the j_{lim} diminution is less drastic, and from pH = 3 the same j_{lim} values as those measured in absence of Br^- are obtained. Furthermore, the onset potential in the presence of Br^- shifts to more positive potential values as pH increases. Additionally, measurements for the HPRR in the same conditions were carried out (Figure 2B) [18]. In all cases the j_{lim} measured for the ORR is higher than the sum of the theoretical j_{lim} for a 2-electron process and the measured current for the HPRR. This difference is especial-

Fig. 2. Comparison between the ORR and the HPRR/HPOR at different pH values for the same limiting current density. The green line represents the theoretical value for j_{lim} . Scan rate: 50 mV/s; rotation rate: 2500 rpm (A). Polarization curves for the ORR (black line) and HPRR (red line) on Pt(111) in the presence of 10^{-2} mol/L KBr in the indicated pH values. Scan rate: 50 mV/s; rotation rate: 2500 rpm. Grey line represents half ($2e^-$) of the theoretical j_{lim} for the ORR ($4e^-$) and the grey dashed line indicates the addition to this value of the experimental j_{lim} obtained for the HPRR. The green line represents theoretical j_{lim} for the ORR (B). Linear sweep voltammograms for the oxygen reduction in O_2 -saturated 0.1 mol/L HClO_4 on stationary Pt(poly) electrodes after conditioning and holding at $E_i = 1.02$ V (OCP) for different resting times τ_h of (a) 0, (b) 1, (c) 5, (d) 15, (e) 30, (f) 45, (g) 60, (h) 90, and (i) 120 s and steady-state cycle for the continuous LSV (dashed line). Scan rate: 0.1 V/s (C). Linear sweep voltammograms for the ORR at Pt(Poly) in O_2 -saturated 0.1 mol/L HClO_4 on RDEs at 2500 rpm after conditioning and holding the potential at $E_i = \text{OCP}$ a resting time $\tau_h = 150$ s. The scan rate is (a) 0.1, (b) 0.8, (c) 2 (D), and (d) 3, (e) 5, (f) 10 V s^{-1} (E). For the sake of comparison steady-state cycles for continuous LSVs (dashed) are also given. Figures 2A and 2B are adapted from [18]. Figures 2C, 2D, and 2E are adapted from Ref. [19].

ly important for pH = 3, where the j_{lim} for the ORR agrees well with the theoretical value (green line in Figure 2B) while the HPRR is markedly inhibited. It is important to remark that the difference between the measured j_{lim} for the ORR and its theoretical value in Figure 2B for pH = 1.1 is due to the presence of Br^- , while the difference in the case of pH = 5.4 is due to the solution pH and j_{lim} is the same in the presence and in the absence of Br^- (see Ref. [18]). All these results indicate that the mechanism for the ORR does not follow a sequential scheme in which H_2O_2 is generated as an intermediate. There must be a bifurcation point that follows a pathway for producing water without the formation of H_2O_2 . This intermediate was also proposed to be $OOH^\bullet$ species [18].

Gómez-Marín et al. [19] also observed evidences of $OOH^\bullet$ intermediate by carrying out experiments under non-steady-state conditions for polycrystalline Pt. Linear sweep voltammetry (LSV) experiments in static conditions after holding the potential at 1.02 V vs. RHE during different resting times pointed out that the peak current density (j_p) is higher for the longest resting times (Figure 2C). In addition, measurements at different scan rates for the same resting time were also performed, and in all cases j_p is higher after holding the potential at the open circuit value during 150 s than the j_p value for the continuous LSV in steady state (Figure 2D). The authors suggested that $OOH^\bullet$ soluble species are formed in a fast initial chemical reaction, and equilibrium is reached in such a way that no currents are measured at potentials higher than

the onset potential. Once the onset potential is attained, this intermediate species would be reduced yielding the next reaction intermediates [19].

4. Spectroelectrochemical and computational methods for intermediates identification

As mentioned in the Introduction section, one of the most difficult challenges during the investigation of the ORR is the detection and identification of the reaction intermediates. The use of spectroelectrochemical methods together with theoretical studies is a common tool for determining these intermediates [11], but in the case of the ORR the detection limits of these techniques are usually too high. However, a recent study using the shell-isolated nanoparticle-enhanced Raman spectroscopy (SHINERS) with the Pt basal planes electrodes in acid and alkaline media proves the identification of ORR intermediates. This spectroelectrochemical technique consists on modifying the Pt surface with gold nanoparticles coated by an ultrathin and uniform silica shell. These nanoparticles are able to strongly enhance the Raman signal of molecules situated near the nanoparticle surface. By using this enhancing strategy the detection limits are suitable for the detection of ORR intermediates.

Figure 3A shows the SHINERS spectra at different potential values for Pt(111) in 0.1 mol/L $HClO_4$ O_2 -saturated solutions. It can be seen that a band at 732 cm^{-1} appears from 0.8 V vs. RHE when potential diminishes. The evolution of the band with the

Fig. 3. EC-SHINERS spectra of the ORR system at a Pt(111) electrode surface in a 0.1 mol/L $HClO_4$ solution saturated with O_2 (A). Normalized EC-SHINERS intensities of the stretching mode of O-OH around 732 cm^{-1} at different potentials and polarization curve of the ORR process at the Pt(111) surface in a 0.1 mol/L $HClO_4$ solution saturated with O_2 . Scan rate: 50 mV/s; rotation rate: 1600 rpm (B). The arrows in both figures A and B represent the potential scanning direction and all potentials are relative to the RHE. Side-view illustrations of $OOH^\bullet$ at a stable configuration at a Pt(111) surface on bridge site adsorption structure (C). EC-SHINERS spectra of the ORR system at Pt(100) (D) and Pt(110) (E) electrodes surface in a 0.1 mol/L $HClO_4$ solution saturated with O_2 . Adapted from Ref. [12].

electrode potential and its comparison with the voltammetric results are shown in Figure 3B. The frequency for the O–O stretching vibration for $\text{OOH}^\bullet$ species in the bridge configuration on Pt(111) (Figure 3C) was calculated by density functional theory (DFT) and the obtained result was 726 cm^{-1} . This value agrees well with the observed band for the SHINERS spectra, and therefore it was proposed that $\text{OOH}^\bullet$ is a reaction intermediate for the ORR on Pt(111). This is the first case of an experimental evidence for the existence of $\text{OOH}^\bullet$ intermediate. Analogous measurements were carried out for Pt(100) and Pt(110), and in these cases no band at ca. 730 cm^{-1} was observed (Figures 3D and 3E). Therefore, $\text{OOH}^\bullet$ would be an intermediate only for Pt(111). Instead, a band at ca. 1080 cm^{-1} was observed for both electrodes (Figures 3D and 3E). By comparison with the DFT calculations results these bands were attributed to Pt–OH bending mode. In light of these results, they proposed a mechanism in which O_2 forms $\text{OOH}^\bullet$ by a proton and an electron transfer. The dissociation energy for this intermediate to form adsorbed O and OH is 1.61 eV on Pt(111), while on Pt(100) this dissociation energy is 0.51 eV (no dissociation energy data is provided for Pt(110) but it is stated that it is also unstable in comparison with Pt(111) [12]). Therefore, $\text{OOH}^\bullet$ intermediate would be more stable and would need a higher activation energy for dissociating into O and OH on Pt(111) than on Pt(100) or Pt(110). This is in agreement with previous theoretical works [20]. Therefore, it is possible to detect it on Pt(111) while in Pt(100) and Pt(110) the O–O breaks quickly making more difficult its observation. These differences between Pt(111) and the other basal planes could also be related with the specific effect of the surface charge. It has been pointed out in section 2 that a different electrocatalytic behavior with pH is observed for Pt(111) due to the fixed pzfc from acid to neutral pH values and the more labile adsorbed OH layer. This could also determine the fact that $\text{OOH}^\bullet$ in Pt(111) is more stable than in Pt(100) and Pt(110). Additional measurements in alkaline media ($\text{pH} = 10$) were performed and the superoxide species (O_2^-) was detected for the three basal planes.

The adsorption behavior of oxygen and the reaction intermediates for the ORR has been extensively studied by theoretical calculations during the last years. The adsorption and dissociation processes of ORR intermediates on the three basal planes have been discussed recently in the work by Dong et al. [12]. DFT results point out that the bridge configuration is the most stable adsorption mode for $\text{OOH}^\bullet$ intermediate on Pt(111) (Figure 3C). As mentioned above, $\text{OOH}^\bullet$ intermediate is less stable on Pt(110) and Pt(100). In the case of adsorbed O and OH intermediates on Pt(100) and Pt(110), it was proposed that OH species are adsorbed on top and the adsorbed O atom on the nearest neighbor contributes bending the H atom. The bridge adsorption mode was calculated to be more stable, but the frequency did not correspond with the experimental value measured by EC-SHINERS. Calculations for H_2O_2 showed that a pathway through the formation of this intermediate would be hindered [20]. However, theoretical calculations may not take into account factors such as the surface charge or the surroundings which could alter the formed intermediates, as dis-

cussed in the next section.

5. ORR mechanism according to the recent results

In light of the previously described studies, the mechanism in Figure 4 is proposed. First, the initial chemical step can take at potential values more positive than the onset potential to form the soluble $\text{OOH}^\bullet$ species. Once the onset potential is reached the O_2 molecule can be reduced also to the $\text{OOH}^\bullet$ intermediate. There is an effect of the surface structure in the ORR mechanism: the $\text{OOH}^\bullet$ intermediate is more stable in Pt(111) and therefore it can be detected by the EC-SHINERS technique, while in Pt(100) and Pt(110) its lifetime is smaller and cannot be detected. This could be due to the different adsorption energy of the intermediates on the basal plane orientations or to the effects of the surface charge. As has been already pointed out, surface charge has an effect on the electrocatalytic activity, and therefore it can affect the mechanism. However, at more neutral pH the decrease on j_{lim} can also be observed on Pt(100) and Pt(110), and this suggests that $\text{OOH}^\bullet$ intermediate could be more stable on the latter surfaces in these conditions. On the other hand, the results from the ORR measurements in the presence of bromides suggested that in very acidic solutions the path in which $\text{OOH}^\bullet$ is reduced to H_2O_2 is preferred, while for more neutral pH values the mechanism follows a pathway in which H_2O_2 would not be formed. For solutions with low ionic strength, the H_2O_2 pathway is also favored. When Br^- anions are present in the solution, the reduction of H_2O_2 is hindered, and therefore the latter is the final product of the reaction. Lastly, when the solution pH is increased towards more neutral values, the reduction of the $\text{OOH}^\bullet$ intermediate is hindered, and it goes to the bulk solution giving thus a decrease in the faradaic efficiency.

6. Perspectives and conclusions

In this report the most recent advances for improving the

Fig. 4. Proposed scheme mechanism for the ORR on Pt electrodes. (*) Predominant at $2 < \text{pH} < 3$ and high ionic strength. Unaffected by Br_{ads} . This reaction is more favored in Pt(100) and Pt(110) than in Pt(111), and therefore the lifetime of $\text{OOH}^\bullet$ is larger on Pt(111) in acidic media. (†) Favored at very acidic pH and low ionic strength. (‡) Hindered in presence of Br_{ads} .

knowledge on the ORR on Pt electrodes have been revised, especially in terms of the effect of the surface charge and the possible mechanism pathways. The electrode surface charge influences the kinetics for the ORR especially in the case of Pt(111), for which the maximum activity is expected to take place at pH = 9. For this pH value, the pzfc for this surface would be very close to the onset potential for the ORR. The dependence is different for Pt(100) and Pt(110) due to the more rigid layer of adsorbed OH at low potentials, while for stepped surfaces the situation is intermediate. In the case of the HPRR, it was demonstrated that the inhibition that takes place at low potentials on Pt(111) is directly related to the pme of the surface, and therefore to the pzfc. Recent results point out that the HPRR is sensitive to the local pme of terraces and steps on Pt stepped surfaces.

It can be observed that the behavior of the ORR and the HPRR with pH is different: while for the HPRR the limiting current density is not affected, the latter decreases as the solution pH is increased for the ORR. In addition, when both reactions are studied in the presence of Br⁻ it can be seen that the HPRR is more inhibited than the ORR, especially at neutral pH values. The solution ionic strength also affects in a different way these reactions. All these results suggest that there exists a bifurcation point in the ORR mechanism prior the formation of H₂O₂. This bifurcation point has been proposed to be OOH[•] species. This intermediate could exist as a soluble species and it has been demonstrated that it can be formed from an initial chemical step. EC-SHINERS measurements and DFT calculations allowed the identification of the OOH[•] intermediate on Pt(111) in acidic media. This intermediate is more stable in Pt(111) than in Pt(100) and Pt(110) as indicated by the obtained dissociation energies and thus pointing out a surface structure effect.

The fundamental knowledge of the ORR is mandatory in order to develop electrode materials with the better performance from a rational strategy. Theoretical calculations are always carried out using model surfaces. The results derived from them cannot be compared with experiments performed with practical polyoriented surfaces. Direct relationships between the theoretical studies and the experimental measure-

ments can only be established when well-oriented surfaces are used, allowing to establish whether calculations are truly representative of the experimental situation. In this sense, the use of Pt single electrodes provides valuable information that can be extrapolated to nanoparticles and therefore to electrocatalysts that can be used in practical applications. Therefore, although the single-crystals electrode cannot be used in practical applications, studies with well-oriented surfaces are important in order to achieve a complete fundamental knowledge of electrocatalytic reactions so that the best practical conditions are established. Further experiments with Pt stepped surfaces, which have step sites with a low coordination and a more similar behavior to the less coordinated sites in practical electrodes, and preferentially oriented Pt nanoparticles will be performed in order to obtain more information about how the surface charge affects the ORR and the HPRR and to gain more details about the mechanism of these reactions.

Acknowledgments

This work was supported by the MINECO-FEDER (project CTQ2016-76221-P). Valentín Briega-Martos thankfully acknowledges to MINECO the award of a predoctoral grant (BES-2014-068176, project CTQ2013-44803-P).

Juan M. Feliu
Instituto de Electroquímica, Universidad de Alicante, Apdo. 99,
E-03080 Alicante, Spain
Tel: +34-96-590-9301
Fax: +34-96-590-3537
E-mail: juan.feliu@ua.es
Received 28 June 2019
Published 05 May 2020
DOI: S1872-2067(19)63325-5

References

- [1] A. M. Gómez-Marín, R. Rizo, J. M. Feliu, *Catal. Sci. Technol.*, **2014**, *4*, 1685–1698.

Graphical Abstract

Chin. J. Catal., 2020, 41: 732–738 doi: S1872-2067(19)63325-5

Recent progress on oxygen and hydrogen peroxide reduction reactions on Pt single crystal electrodes

Valentín Briega-Martos, Enrique Herrero, Juan M. Feliu *
Universidad de Alicante, Spain

The most recent advances for the ORR in Pt single crystal electrodes are summarized. A mechanism for the reaction is presented in light of the recent results.

- [2] A. Damjanovic, M. A. Genshaw, J. O. M. Bockris, *J. Electrochem. Soc.*, **1967**, 114, 466–472.
- [3] N. M. Markovic, H. A. Gasteiger, P. N. Ross Jr, *J. Phys. Chem.*, **1995**, 99, 3411–3415.
- [4] L. Zhang, H. Li, J. Zhang, *J. Power Sources*, **2014**, 255, 242–250.
- [5] J. Greeley, J. Rossmeisl, A. Hellman, J. K. Nørskov, *Zeitschrift fuer Physikalische Chemie (Muenchen, Germany)*, **2007**, 221, 1209–1220.
- [6] M. D. Maciá, J. M. Campina, E. Herrero, J. M. Feliu, *J. Electroanal. Chem.*, **2004**, 564, 141–150.
- [7] A. Kuzume, E. Herrero, J. M. Feliu, *J. Electroanal. Chem.*, **2007**, 599, 333–343.
- [8] A. M. Gómez-Marín, J. M. Feliu, *Catal. Today*, **2015**, 244, 172–176.
- [9] R. Rizo, E. Sitta, E. Herrero, V. Climent, J. M. Feliu, *Electrochim. Acta*, **2015**, 162, 138–145.
- [10] A. M. Gómez-Marín, J. M. Feliu, *ChemSusChem*, **2013**, 6, 1091–1100.
- [11] S. Nayak, I. J. McPherson, K. A. Vincent, *Angew. Chem. Int. Ed.*, **2018**, 57, 12855–12858.
- [12] J. C. Dong, X. G. Zhang, V. Briega-Martos, X. Jin, J. Yang, S. Chen, Z. L. Yang, D. Y. Wu, J. M. Feliu, C. T. Williams, Z. Q. Tian, J. F. Li, *Nat. Energy*, **2019**, 4, 60–67.
- [13] R. Martínez-Hincapié, V. Climent, J. M. Feliu, *Curr. Opin. Electrochem.*, **2019**, 14, 16–22.
- [14] P. Sebastián, R. Martínez-Hincapié, V. Climent, J. M. Feliu, *Electrochim. Acta*, **2017**, 228, 667–676.
- [15] V. Briega-Martos, E. Herrero, J. M. Feliu, *Electrochim. Acta*, **2017**, 241, 497–509.
- [16] V. Briega-Martos, E. Herrero, J. M. Feliu, *Electrochem. Commun.*, **2017**, 85, 32–35.
- [17] N. Garcia-Araez, V. Climent, J. M. Feliu, *Electrochim. Acta*, **2009**, 54, 966–977.
- [18] V. Briega-Martos, G. A. B. Mello, R. M. Arán-Ais, V. Climent, E. Herrero, J. M. Feliu, *J. Electrochem. Soc.*, **2018**, 165, J3045–J3051.
- [19] A. M. Gómez-Marín, J. M. Feliu, E. A. Ticianelli, *ACS Catal.*, **2018**, 8, 7931–7943.
- [20] J. A. Keith, T. Jacob, *Angew. Chem. Int. Ed.*, **2010**, 49, 9521–9525.

Pt单晶电极上氧和过氧化氢还原反应研究进展

Valentín Briega-Martos, Enrique Herrero, Juan M. Feliu^{*}

阿利坎特大学电化学研究所, 阿利坎特, 西班牙

摘要: 氧还原反应(ORR)可能是电催化中最重要的阴极过程。尽管最近几年有关ORR反应的实验和理论研究很多, 但ORR反应完整的机理尚未完全阐述清楚。本文总结了在单晶Pt电极上ORR反应研究的最新进展, 特别是有关表面电荷的影响和可能的反应路径, 并基于这些研究结果给出了ORR反应机理。

关键词: 疏基金纳米簇; 金属氧化物载体; 疏基配体; 一氧化碳氧化

收稿日期: 2019-06-28. 接受日期: 2019-08-13. 出版日期: 2020-05-05.

*通讯联系人. 电话: +34-96-590-9301; 传真: +34-96-590-3537; 电子信箱: juan.feliu@ua.es

本文的电子版全文由Elsevier出版社在ScienceDirect上出版(<http://www.sciencedirect.com/science/journal/18722067>).